## **MULTIS EP 1**



Grease



## Multi purpose extreme pressure lithium/calcium grease.

		J			
APPLICATIONS					
Multi purpose EP grease General Lubrication Recommendation	and roller-bea or vibrating ap dusty and/or c	eneral purpose grease for industrial application	ssis, and various bad equipment, op	shock loaded perating in wet,	
Recommendation	<ul> <li>Always avoid of</li> </ul>	contamination of the grease by dust and/or o pump system or cartridges.	dirt when applying	. Preferably use	
SPECIFICATION	S				
	● ISO 6743-9: L- ● DIN 51 502: K				
ADVANTAGES					
Durable film Miscible Mechanical stability Thermal stability No harmful substances	<ul> <li>Because of its true Multi Purpose character MULTIS EP 1 may replace a wide range of greases, allowing stock rationalization and simplification of maintenance.</li> <li>Forms a durable lubrication film, resulting in reduction of maintenance and down-time costs.</li> <li>Miscible with most other conventional soap greases.</li> <li>Excellent mechanical stability avoiding ejection or loss of consistency during operation.</li> <li>Excellent adhesion to metal.</li> <li>Good thermal stability, leading to high resistance to temperature variations.</li> <li>MULTIS EP 1 does not contain lead, or other heavy metals considered harmful to human health and the environment.</li> </ul>				
TYPICAL CHARACT	ERISTICS	METHODS	UNITS	MULTIS EP 1	
Soap/thickener			-	Lithium/ Calcium	

Soap/thickener		-	Lithium/ Calcium
NLGI grade	ASTM D 217/DIN 51 818	-	1
Color	Visual	-	Pale brown
Appearance	Visual	-	Smooth
Operating temperature range		°C	- 25 to 120
Penetration at 25°C	ASTM D 217/DIN51 818	0.1 mm	310 -340
Four ball weld load	DIN 51 350-4	daN	260 - 280
Anti-rust performance SKF- EMCOR	DIN 51 802/IP220/NFT 60-135/ISO 11007	rating	0 - 0
Dropping point	IP 396/NFT 60 102 C	°C	> 190
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/IP71	mm²/s (cSt)	150

Above characteristics are mean values given as an information.

TOTAL LUBRIFIANTS Industrie & Spécialités 13-02-2004 (supersedes 17-07-2001) MULTIS EP 1 1/1



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser <u>www.guick-fds.com.</u>